arXiv:1212.0299v1 [cond-mat.str-el] 3 Dec 2012

Phenomenological model for the normal state ARPES line shapes of high temperature superconductors

Kazue Matsuyama[1] and G.-H. Gweon[1, *]

[1]*Department of Physics, University of California, Santa Cruz, CA 95064*

(Dated: December 4, 2012)

An adequate description of the single particle spectral function observed in high temperature superconductors in the normal state is an important goal, yet to be realized. Here, we show that with minimal phenomenological extension of the so-called extremely correlated fermi liquid (ECFL) model, it is possible to establish a phenomenological model, which is capable of describing ARPES data for different materials ($Bi_2Sr_2CaCu_2O_{8+\delta}$ and $La_{2-x}Sr_xCuO_4$), with exceptional fidelity in fitting the data as function of momentum as well as energy.

PACS numbers: 71.10.Ay,74.25.Jb,74.72.Gh,79.60.-i

In the sudden approximation theory [1] of the angle resolved photo-electron spectroscopy (ARPES), photoelectron counts, $I(\vec{k},\omega)$, recorded as a function of momentum ($\vec{k}$) and energy (ω)[2] are given by

$$I(\vec{k},\omega) = |M_{if}|^2 \, f(\omega) \, A(\vec{k},\omega) \qquad (1)$$

where M_{if} is the dipole matrix element for the photoexcitation, $f(\omega)$ is the Fermi-Dirac distribution function, and $A(\vec{k},\omega)$ is the single particle spectral function, $A(\vec{k},\omega) = \frac{1}{\pi}\mathrm{Im}\, G(\vec{k},\omega)$, where G is the single particle Green's function[3].

As the single particle Green's function in the normal state contains vital information on the nature of excitations relevant to the high temperature ("high T_c") superconductivity, its characterization by ARPES has been a major line of research. Various approaches towards getting at this information have been attempted: a phenomenological approach based on a simple scaling behavior of the electron self energy [4], an asymptotic solution to the Gutzwiller projected ground state of the t-J Hamiltonian [5], application of a non-Fermi liquid theory [6] for low dimensions, and a newly proposed solution to the t-J Hamiltonian [7].

For an experimental "cut," i.e. an experimental data set taken along a line of $\vec{k}$ values, $I(\vec{k},\omega)$ is a function defined on a two dimensional domain. This multidimensionality makes analyzing $I(\vec{k},\omega)$ a non-trivial task. While attempts [8] have been made to analyze the $I(\vec{k},\omega)$ image (e.g., see Figure 3(a)) as a whole, the current theoretical understanding of line shapes in terms of $A(\vec{k},\omega)$ depends on the analysis of selected energy distribution curves (EDCs; EDC means $I(\vec{k},\omega)$ as a function of ω for a fixed value of $\vec{k}$) [4, 5, 7, 9] or selected momentum distribution curves (MDCs; MDC means $I(\vec{k},\omega=\omega_0)$ with a constant ω_0 and $\vec{k}$ along a line) [9, 10].

Currently, there is no consensus on a theoretical model that can suitably describe ARPES data of high T_c materials. A model that can describe the normal state data, both EDCs and MDCs, obtained in different experimental conditions and for different materials with the same intrinsic parameters would be a good candidate. Here, we propose a new phenomenological model that satisfies just such a requirement. This model is built upon the recent success of the so-called extremely correlated Fermi liquid (ECFL) model [7]. This model retains all features of this past work, but with crucial extension that makes the model suitable for describing MDCs as well.

The result is a phenomenological model in which an *intrinsic inelastic background* ("caparison factor") due to extreme electron correlations [7, 11] continues to play a critical role in fitting EDCs while the effect of the caparison factor on MDCs is significantly reduced, suggesting an interesting dichotomy between the behaviors of the EDC and the MDC, somewhat reminiscent of a similar dichotomy observed in low dimensional systems [6, 12].

A phenomenological study of this kind seems to be helpful, also in light of the on-going development of the ECFL theory [13, 14]. The theoretical formalism of ECFL initiated by Shastry [11, 13] is quite involved, and, while a numerical solution [14] valid for hole doping $x \gtrsim 0.3$ is now available, more time seems necessary to extend these promising results to near-optimal doping. Thus, a phenomenological model based on the main feature of the theory, the caparison factor, may be of considerable value at this stage. In this theory [13], the caparison factor is an *ω-dependent adaptive spectral weight* that encodes two key pieces of physics: the Gutzwiller projection that reduces the spectral weight at high ω and the invariance of the Fermi surface volume at low ω.

In our previous work [7], it has been demonstrated that the normal state EDCs for optimally doped cuprates for two different compounds, or for different experimental conditions (low photon energy or high photon energy), can be explained using an ECFL line shape model, all with one set of intrinsic parameters. We will refer to that model as the "simplified ECFL (sECFL)" model [15], in relation to the fuller theory in development [13, 14]. While the EDC analysis, the focus of Ref. 7, has strong merits [7, 16], a natural subsequent question is whether MDCs can be described as well within the same theory.



FIG. 1. Line shape fits of EDCs for Bi2212 using (a) sECFL, (b) pECFL with momentum dependence (MD), and (c) pECFL with momentum independence (MI). Data and model parameters are identical with those in Ref. 7, except for additional parameters used for (b), $a_1 = 1.2$ and $a_2 = 2.5$ (cf. Eq. 6), and a slightly different η value ($0.17 \rightarrow 0.18$ eV).

In the sECFL model [7], the Green's function was taken to be of the form

$$G(\vec{k},\omega) = \frac{Q_n - \frac{n^2}{4}\frac{\Phi(\omega)}{\Delta_0}}{\omega - \varepsilon(\vec{k}) - \Phi(\omega)} \tag{2}$$

where $Q_n = 1 - \frac{n}{2} = \frac{1+x}{2}$ is the total spectral weight per $\vec{k}$ in the t-J model, n is the number of electrons per unit cell, and $x = 1 - n$ is the hole doping per unit cell, $\Phi(\omega)$ is an ordinary Fermi liquid self energy (Eq. 2 and footnote 6 of Ref. 7) containing two intrinsic parameters, Z_{FL} and ω_0, and one extrinsic parameter, η. Δ_0 is the energy scale that is uniquely determined by n, Z_{FL}, ω_0 through the global particle sum rule [17].

The above Green's function can be rewritten as

$$G(\vec{k},\omega) = \frac{Q_n}{\gamma_n} + \frac{\mathcal{C}_n(\vec{k},\omega)}{\omega - \varepsilon(\vec{k}) - \Phi(\omega)} \tag{3}$$

$$\mathcal{C}_n(\vec{k},\omega) = Q_n\left(1 - \frac{\omega - \varepsilon(\vec{k})}{\gamma_n}\right) \tag{4}$$

where $\mathcal{C}_n(\vec{k},\omega)$ is the "caparison factor" [7, 11] and $\gamma_n \propto \Delta_0$ is an energy scale parameter, to be discussed further below. As all symbols in Eq. 3 other than $\Phi(\omega)$ are real,

$$A(\vec{k},\omega) = \mathcal{C}_n(\vec{k},\omega)\, A_{FL}(\vec{k},\omega) \tag{5}$$

where A_{FL} is the spectral function for the "auxiliary Fermi liquid (AFL)" Green's function [18], $A_{FL} = \frac{1}{\pi}\,\mathrm{Im}\, G_{FL} = \frac{1}{\pi}\,\mathrm{Im}\,[\omega - \varepsilon(\vec{k}) - \Phi(\omega)]^{-1}$.

We will show how the function $\mathcal{C}_n$ can be modified phenomenologically so that the main sECFL idea, summarized concisely in Eqs. 4 and 5, can be fully preserved while the range of applicability of the model can be extended in a critical manner. We shall refer to the modified model as pECFL, with p for "phenomenological."

We begin our discussion by showing line shape fit results first, and will then explain our new model.

Figure 1 shows ARPES line shape fits for the normal state data for the optimally doped $Bi_2Sr_2CaCu_2O_{8+\delta}$ (Bi2212) sample along the "nodal direction," $(0,0) \rightarrow (\pi,\pi)$. The data are identical with the data discussed in Figure 4(b) of our previous work [7]. Panel a shows the sECFL fit essentially[19] identical with the fit in that work, while panels b,c show pECFL fits. With pECFL, the fit quality remains equally excellent for $k \approx k_F$, while, for k away from k_F, it has improved noticeably, albeit by small amount (e.g., see the EDC at top or bottom).

Figure 2 shows ARPES line shape fits for MDCs of the same data set. Panel a shows clearly that sECFL has difficulty fitting the data even for $\omega = 0$, i.e. the Fermi energy (E_F). In panel b, where the pECFL(MD) model is used, the fit improves visibly. However, the quality of the fit of panel c, where the pECFL(MI) model is used, is clearly the best.

We note that for the data fit in Figures 1 and 2 a small "elastic background line shape" (0.5 times the raw line shape for $k \gg k_F$) had been subtracted, as explained in Ref. 7. Then, the data are fit fully with the spectral weight given by Eq. 1 without any additional background intensity at all. That the model pECFL(MI) is able to describe both EDCs and MDCs in this manner, with completely identical parameter values, including the η value, demonstrates the high fidelity of the model. In contrast, it is impossible to achieve optimal fits of MDCs



FIG. 2. Line shape fits of MDCs for Bi2212 using (a) sECFL and (b) pECFL(MD) and (c) pECFL(MI). Fit parameters are the same as those used for Fig. 1, except for the η values for (a,b), as noted here.

and EDCs with the same η parameter within sECFL or pECFL(MD): as shown at top of panels a,b, the fit quality degrades significantly if the same η value as that for EDCs is used. These conclusions remain the same for the fit of the 91 K data [7][20].

Now, we explain our new model, and its two regimes ("MD" and "MI").

From Eq. 5, it is required that $\mathcal{C}_n(\vec{k},\omega) \geq 0$ for any value of $\vec{k}$ and ω, or equivalently $\gamma_n \geq \omega - \varepsilon(\vec{k})$. For $\gamma_n > 0$, it can be seen that this condition is satisfied sufficiently close to the Fermi energy ($\omega = 0$) and the Fermi momentum ($\varepsilon(\vec{k}) = 0$). On the other hand, for a negative value of $\varepsilon(\vec{k})$, $\omega - \varepsilon(\vec{k})$ becomes increasingly more positive where important spectral features are expected: as the peak position is given by $\omega \approx Z\varepsilon(\vec{k})$ with the mass renormalization ratio $0 \leq Z < 1$, we see that $\omega - \varepsilon(\vec{k})$ grows as $\approx (1-Z)|\varepsilon(\vec{k})|$, as $\varepsilon(\vec{k})$ decreases from 0.

In the sECFL model, γ_n is given by $4Q_n\Delta_0/n^2$, which we shall define as γ_{n0}. For our fit parameters [7], $\Delta_0 = 0.12$ eV, $n = 0.85$, we get $\gamma_{n0} = 0.38$ eV. Since $Z_{FL} = 1/3$ [7] and thus $Z = Z_{FL}Q_n = 0.19$, we see that $\mathcal{C}_n \geq 0$ requires that $\varepsilon(\vec{k}) \gtrsim -0.47$ eV. For the data fit in Figure 1, the smallest $\varepsilon(\vec{k})$ value is -0.4 eV for $k = k_1$, as shown in Figure 3(a). Thus, the simple truncation procedure, ($\mathcal{C}_n \to \max(\mathcal{C}_n, 0)$), put in place for the sECFL in Ref. 7 to assure the positivity of the spectral function, was justified.

How might the model be modified so that it is suitable for describing MDCs at low energy as well, while it preserves, or improves, the quality of EDC fits? As we showed in the above figures, a dramatic improvement of MDC fits and a substantial improvement of EDC fits *can* be achieved at the same time. While the improvement of the EDC fit quality is arguably only modest for the fits shown in Figure 1, it is clear from the above discussion that the improvement will be dramatic outside the momentum range shown in Figure 1. Figure 3(b) shows that this is indeed the case.

Our new pECFL model is based on two generic observations: (i) from a more fundamental point of view [21], going beyond sECFL, γ_n can be dependent on both $\varepsilon(\vec{k})$ and ω, and (ii) MDCs observed for high T$_c$ cuprates tend to be fit well with Lorentzian line shapes in general (but see Figure 4).

With these observations, the following can be noted. Considered as a function of $\omega - \varepsilon(\vec{k})$, $\mathcal{C}_n$ needs modification only in the limit of $\omega - \varepsilon(\vec{k}) \to \infty$. If γ_n is taken to be a function of ω and $\varepsilon(\vec{k})$, this can be accomplished by requiring that $1/\gamma_n \to 0$ as $\omega - \varepsilon(\vec{k}) \to \infty$. We keep $\gamma_n = \gamma_{n,0}$ for the opposite limit $\omega - \varepsilon(\vec{k}) \to -\infty$. This minimal modification of the model has the additional virtue of establishing the correct limiting behavior $G(\vec{k},\omega) \to Q_n/\omega$ for $\omega \to \infty$, as well as for $\omega \to -\infty$, as required by the sum rule [22] per $\vec{k}$, within the t-J model.



FIG. 3. (a) The ARPES data for Bi2212, used for previous figures. Rectangle E (M) marks the range of data fit in Figure 1 (2). Circle symbols show $\varepsilon(\vec{k})$ values [7] used in the fits. The color scale represents ARPES counts that increase from green, blue (half max), white, to red (max). (b) The EDC fits for the k value corresponding to line V of panel a. (c) The caparison factors ($\mathcal{C}_n(\vec{k},\omega)$). In pECFL(MI), we take $\mathcal{C}_n(k = k_F, \omega)$ of sECFL, or pECFL(MD), and apply it to *any* $\varepsilon(\vec{k})$. (d,e) The weights determined from MDC fits (d) and EDC fits (e). Rectangular shades mark the ω-range (d) and the k-range (e) corresponding to fits in Figures 1,2, respectively.

A simple way to implement the modification is to use a sigmoidal reduction of $1/\gamma_n$ as $\omega - \varepsilon(\vec{k}) \to \infty$:

$$\gamma_n = \gamma_{n0} \cdot \left[1 + \exp\left(\frac{\omega - \varepsilon(\vec{k}) - a_1\gamma_{n0}}{a_2\gamma_{n0}}\right)\right] \tag{6}$$

The model that incorporates this γ_n function is named "pECFL(MD)," where MD means "with momentum dependence," as $\mathcal{C}_n(\vec{k},\omega)$ is dependent [23] on $\vec{k}$ through $\varepsilon(\vec{k})$.

The role of the two new parameters, a_1 and a_2, is to provide "soft landing" to the caparison factor. With good values of a_1 and a_2, the caparison factor never dips below zero, and approaches zero only asymptotically, from above, as $\omega - \varepsilon(\vec{k}) \to \infty$. The key is that the soft landing must be engaged early (small a_1), but not too early, and quickly (small a_2), but not too abruptly. After some calculus, one sees that the success, i.e. the non-negativity of $\mathcal{C}_n$ for any value of $\omega - \varepsilon(\vec{k})$, is guaranteed if

$$a_1 \leq 1 + a_2\,(1 - \log a_2) \,\equiv\, a_{1,max}(a_2) \tag{7}$$

This condition was used as a constraint during the line shape fit using the pECFL(MD) model. In practice, we find that only very narrow ranges of possible a_1 and a_2 values are allowed: both must be of order 1.

Another regime for pECFL is motivated by the observation (ii) above. Lorentzian-like MDCs can be taken to mean a momentum independent self energy[24]. This motivates us to consider simply dropping the $\varepsilon(\vec{k})$ term in Eq. 4, and obtain a momentum-independent version of sECFL, which we call "pECFL(MI)." However, since we are concerned only with ARPES fits here ($\omega \lesssim 0$), pECFL(MI) can also be thought of as a momentum-independent version of pECFL(MD), whose caparison factor for $\varepsilon(\vec{k}) = 0$ and $\omega \lesssim 0$ is practically identical with that of sECFL for the same parameters, as shown in Figure 3(c).

Lastly, the quality of line shape fits can be examined by inspecting the weight parameter that determines the overall scale: $w_m(\omega) \equiv |M|^2 f(\omega)$ for MDC fits, shown in Figure 3(d), and $w_e(k) \equiv |M|^2$ for EDC fits, shown in Figure 3(e). In this figure, these functions are shown for ranges of ω and $\vec{k}$ going beyond the ranges for Figures 1 and 2. As the energy dependence of $|M|^2$ is expected to be weak for the narrow range of ω used in the fit, we expect that the shape of $w_m(\omega)$ be determined mostly by $f(\omega)$ alone, which we show for comparison in Figure 3(d). Also, we expect that $w_e(k)$ show only modest variation in the momentum range of the fit [8, 25]. It is clear that these expectations are met increasingly better as we go from sECFL, to pECFL(MD), and to pECFL(MI). For example, for sECFL, $w_m(\omega)$ deviates strongly from $f(\omega)$ for $\omega < -50$ meV, and $w_e(\omega)$ increases by more than an order of magnitude as $|k|$ decreases.

Therefore, for the Bi2212 data examined, pECFL(MI) emerges as the best model. However, that this may not be a universal behavior is indicated in Figure 4. Here, the EDC data and the MDC data for $La_{2-x}Sr_xCuO_4$ samples, as we found available in the literature [26, 27], are fit. For the pECFL(MD), $a_1 = 1.6$ and $a_2 = 2.0$ are used, while all other parameters are the same as those for Bi2212, except the different doping parameter $n = 0.937$ necessary for panels d-f. For panels a-c, $\omega_0 = 0.42$ eV is used, the value found [7] to fit the data to very high $|\omega|$ value, compared to $\omega_0 = 0.5$ eV, equally good for fitting data up to $|\omega| \approx 0.25$ eV, just as for Bi2212.

Panels a-c of Figure 4 show that the EDC at k_F is described well by all models [28], as we found for Bi2212. The MDC fits ($\omega = 0$; panels d-f) however give an edge to pECFL(MD), compared to both sECFL and pECFL(MI): it gives half as small χ^2. Key observation is that the MDC at $\omega = 0$ *is notably asymmetric.*



FIG. 4. EDC fits to the LSCO data (a-c, optimally doped, $n = 0.85$), and MDC fits to the LSCO data (d-f, under doped, $n = 0.937$). The data for (a-c) are the same as those used in Figure 4(c-d) of Ref. 7, while the MDC data in (d-f) are taken from Ref. 27.

In conclusion, in this Letter, we propose a phenomenological ARPES line shape model based on the ECFL approach. The essential characteristic of the model remains the caparison factor [7], which is modified in this Letter to excellently describe both EDCs, characterized by strong asymmetry, and MDCs, seemingly more "conventional," much more so for Bi2212. While our model is not the first to fit both EDCs and MDCs [9] of high T$_c$ cuprates, its demonstrated fidelity and range of applicability is now unprecedented. In addition, continuing first principle studies [14] indicate that the interplay between the extreme correlation and the one electron band structure (e.g., the t'/t ratio) may be important – we hope to learn whether such interplay accounts for certain material dependence that we are beginning to recognize here. More experiments and line shape analysis, in coordination with theory development, may shed light on this and other remaining questions such as momentum dependence and doping dependence.

We gratefully acknowledge B. S. Shastry and D. Hansen for stimulating discussions and feedback to the manuscript, and G. D. Gu for $Bi_2Sr_2CaCu_2O_{8+\delta}$ samples used for the original data [7]. The work by GHG was supported partially by COR-FRG at UC Santa Cruz. Portions of this research were carried out at the SSRL, a Directorate of SLAC National Accelerator Laboratory and an Office of Science User Facility operated for the U.S. DOE Office of Science by Stanford University.

---

[*] corresponding author, gweon@ucsc.edu.

[1] L. Hedin and S. Lundqvist, in *Solid State Physics*, Vol. 23, edited by F. Seitz, D. Turnbull, and H. Ehrenreich (Academic, New York, 1969) p. 1.
[2] We use the $\hbar = 1$ convention throughout.
[3] We work in the advanced Green's function convention as in Ref. 7.
[4] C. M. Varma *et al.*, Phys. Rev. Lett. **63**, 1996 (1989).
[5] P. W. Anderson, Phys. Rev. B **78**, 174505 (2008).
[6] D. Orgad *et al.*, Phys. Rev. Lett. **86**, 4362 (2001).
[7] G.-H. Gweon, B. S. Shastry, and G. D. Gu, Phys. Rev. Lett. **107**, 056404 (2011).
[8] W. Meevasana *et al.*, Phys. Rev. B **77**, 104506 (2008).
[9] A. Kaminski *et al.*, Phys. Rev. B **71**, 014517 (2005).
[10] T. Valla *et al.*, Science **285**, 2110 (1999).
[11] B. S. Shastry, Phys. Rev. Lett. **107**, 056403 (2011).
[12] G.-H. Gweon, J. W. Allen, and J. D. Denlinger, Phys. Rev. B **68**, 195117 (2003).
[13] B. S. Shastry, arXiv:1207.6826 (2012).
[14] D. Hansen and B. S. Shastry, arXiv:1211.0594 (2012).
[15] B. S. Shastry, Phys. Rev. Lett. **108**, 029702 (2012).
[16] P. A. Casey *et al.*, Nat Phys **4**, 210 (2008).
[17] Here, we use the notation $\varepsilon(\vec{k})$ instead of $\xi(\vec{k})$ (Ref. 7) for the one electron energy.
[18] As in Ref. 7, the subscript "FL" means the AFL.
[19] The slight difference is due to a slight change of η noted in the caption of Figure 1.
[20] However, we find that a slightly smaller value of $\eta = 0.16$ eV is better for the simultaneous description of the EDCs and MDCs for data taken at 91 K.
[21] B. S. Shastry, Phys. Rev. B **84**, 165112 (2011).
[22] A. L. Fetter and J. D. Walecka, *Quantum Theory of Many-Particle Systems* (Dover Publications, 2003).
[23] This is true even if γ_n is independent of $\varepsilon(\vec{k})$, i.e., even for sECFL. See Eq. 4.
[24] However, there may be a notable interesting exception [6] to this association.
[25] A. Bansil and M. Lindroos, Journal of Physics and Chemistry of Solids **59**, 1879 (1998).
[26] T. Yoshida *et al.*, J. Phys.: Cond. Matt. **19**, 125209 (2007).
[27] X. J. Zhou, J. Hussain, and Z. X. Shen, Synchrotron Radiation News **18**, 15 (2005).
[28] The EDC fits for the underdoped sample (not shown) lead to the same conclusion, while the fits at high energy ($|\omega| \gtrsim 0.1$ eV) are not as good.